Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

 (Currently amended) A metallic glass alloy having the ratio of elements of the formula [HfaCubNicAldYe] HfaCubNicAldYe, wherein;

Y comprises at least one element from Group IVA, IVB, VA, or VB;

- a is less than 45 atomic percent;
- b is from about 15 to about 35 atomic percent;
- c is from about 5 to about 25 atomic percent;
- d is from about 0 to about 20 atomic percent; and
- e is from about 0 to about 15 atomic percent, wherein a+b+c+d+e=100.
- (Previously presented) The metallic glass alloy of claim 1, wherein a is 44.5 atomic percent or less.
- 3. (Previously presented) The metallic glass alloy of claim 2, wherein Y is Ti or Nb.
- (Previously presented) The metallic glass alloy of claim 1, further comprising a density greater than about 7 g/cm3.
- (Currently amended) The metallic glass alloy of claim 4, wherein the density is about 10.5 g/cm3 [or more].
- (Currently amended) The metallic glass alloy of claim 1, wherein the alloy exhibits a
 distinct glass transition temperature, [which] that is at least 0.59 of the liquidus temperature of the
 alloy.
- (Previously presented) The metallic glass alloy of claim 1, wherein the ratio of Cu to Ni is 2:1.
- (Previously presented) The metallic glass alloy of claim 3, wherein the ratio of Cu to Ni is 2:1.

- (Previously presented) The metallic glass alloy of claim 3, having about 5 or more atomic percent Ti.
- (Previously presented) The metallic glass alloy of claim 3, having about 5 or more atomic percent Nb.
- 11. (Previously presented) The metallic glass alloy of claim 1, wherein d is about 10 or more.
- 12. (Previously presented) The metallic glass alloy of claim 1, wherein 35 < a < 45, 0.1 < d < 20, and 0.1 < e < 15.
- 13. (Previously presented) An article comprising the metallic glass alloy of claim 1.
- 14. (Previously presented) The article of claim 13 having a thickness of at least 1 millimeter in its smallest dimension.
- 15. (Previously presented) The article of claim 13 having a thickness at least 3 millimeters in its smallest dimension.
- 16. (Previously presented) A metallic glass alloy composition comprising:
- 44.5 atomic percent hafnium;
- about 27 atomic percent copper;
- about 13.5 atomic percent nickel;
- about 10 atomic percent aluminum; and
- about 5 atomic percent titanium or niobium.
- (Previously presented) The composition of claim 16 having a density greater than 7 g/cm3.
- (Previously presented) The composition of claim 16, having a density of about 10.9 g/cm3 or more.

- (Previously presented) The composition of claim 16, wherein the composition exhibits a
 distinct glass transition temperature of at least 0.59 of the liquidus temperature of the
 composition.
- 20. (Previously presented) An article comprising the metallic glass alloy of claim 16,
- (Previously presented) The article of claim 20 having a thickness of at least 1 millimeter in its smallest dimension.
- 22. (Previously presented) The article of claim 20 having a thickness of at least 3 millimeters in its smallest dimension.
- (Previously presented) The article of claim 20, wherein the ratio of copper to nickel is
 2:1.
- (Previously presented) The article of claim 20, wherein the metallic glass is at least partially amorphous.
- 25. (Previously presented) The article of claim 20, wherein the article has an elastic strain to failure between about 1.8 and 2.2 percent elongation.
- (Previously presented) The article of claim 20, wherein the object has a quasi-static compressive yield stress of between about 1.8 and 2.2 GPa.
- (Previously presented) The article of claim 20, wherein the object has a dynamic highstrain-rate yield stress of between about 1.3 and 1.6 GPa.
- (Previously presented) A metallic glass alloy comprising Hf, Cu, and Ni in eutectic combination with Al, Ti, Nb or a combination thereof, having a density greater than about 7 g/cm3.
- (Previously presented) A method for forming a metallic glass alloy comprising: combining 44.5 atomic percent hafnium;

Confirmation No. 4322 Amdt. Dated 30 April 2008 Reply to Office Action of October 29, 2007

about 27 atomic percent copper; about 13.5 atomic percent nickel; about 10 atomic percent aluminum; and about 5 atomic percent titanium or niobjum,

- (Previously presented) The metallic glass alloy of claim 1, wherein the alloy is formed by electric are melting.
- (Previously presented) The metallic glass alloy of claim 1, wherein the alloy is formed by induction melting.
- (Previously presented) The article of claim 16, wherein the article is formed by vacuum suction easting.
- (Previously presented) The article of claim 16, wherein the article is formed by permanent mold casting, injection die casting, pour casting, planar flow casting, melt spinning, or extrusion.
- 34. (Currently amended) A method for making an alloy generally represented by the formula
 [HfaCubNieAldYe] Hf₂Cu_bNi_cAlgY_e, wherein Y includes at least one element selected from
 Group IV or Group V transition metal elements, wherein Hf is not equal to Y, Group VA, VIII,
 IVB, or VB, wherein a+b+c+d+c=100% (atomic percent), and a is less than 45 [-an-alloy comprising Hf, Cu, and Ni, wherein preferably 35<a<45, 15<b<35, 5<e<25, 0<d<20, and
 0<e<1.5] in an invariant combination.
- 35. (Previously presented) An alloy according to Claim 34 invariantly combining Hf, Cu, and Ni with Al, and Ti or Nb to form a metallic glass alloy having a density greater than about 7 g/cm3.
- (Currently amended) The alloy of Claim 35 wherein the alloy contains [in euteetie combination with] Al.

Page 6 of 11

- (Currently amended) The alloy of Claim 36 wherein the alloy contains [in euteetie eembination with] Ti or Nb.
- 38. (Currently amended) The alloy of Claim 35 wherein the alloy contains [in euteetic combination with] an element from Group IVA or Group IVB.
- 39. (Currently amended) The alloy of Claim 36 wherein the alloy contains [in-euteetie eembination-with] an element from Group IVA or Group IVB.
- 40. (Newly presented) The alloy of Claim 34 wherein preferably 35<a<45, 15<b<35, 5<e<25, 0<d<20, and 0<e<15.

Page 7 of 11